

## GT-PE GASKET TAPE

### General description

Polyethylene foam

Self-adhesive on one side

Available in 4 and 6 mm thick

Available in width 9, 12 and 15 mm



### Technical specifications

| GT-PE                                    |                                |                             |         |
|--|--------------------------------|-----------------------------|---------|
| BASE                                     | Polyethylene foam              |                             |         |
| ADHESIVE                                 | Synthetic rubber hot-melt      |                             |         |
| RELEASE PAPER                            | Without fixed siliconized foil |                             |         |
| TEMPERATURE RANGE                        | - 30°C to + 80°C               |                             |         |
| RESISTANCE TO HIGH HUMIDITY              | Very good                      |                             |         |
| FOAM                                     |                                |                             |         |
| DENSITY                                  | ISO 845                        | ~ 30 Kg/ m <sup>3</sup>     |         |
| TENSILE STRENGTH                         | ISO 1926                       | Lenghtwise                  | 325 kPa |
|  |                                | Crosswise                   | 220 kPa |
| ELONGATION AT BREAK                      | ISO 1926                       | Lenghtwise                  | 125 %   |
|  |                                | Crosswise                   | 115 %   |
| COMPRESSIVE STRENGTH AT 50 % COMPRESSION | ISO 844                        | 98 kPa                      |         |
| COMPRESSION SET AT 25% / 22H À 23°C      | ISO 1856-B                     | 20 % (0,5h after discharge) |         |
|  |                                | 12 % (24h after discharge)  |         |
| WATER ABSORPTION (7 days)                |                                | < 1 Vol.-%                  |         |

### Application


The surface needs to be clean, dry and free of dust and grease.

### Storage

In a dry place and well ventilated, protected from dust and sunlight, better at a temperature between + 10°C and + 30°C.

Stored in these conditions, the adhesive tapes can be stored for minimum 12 months.

The rolls have to be stored flat and cut in the original packaging.



Information contained herein is based on careful tests and experience. It reflects our knowledge and is for guidance purpose only. It is given in good faith and user should ensure that the product is fit for purpose before any application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Manufacturer and distributor are not responsible for any non-recommended use or consequential damage.5



**NEU 6000, S.A.**

Pol. Ind. "La Torre"  
Av. Joaquim de Barnola i Bassols, 6  
08760 Martorell - Barcelona  
SPAIN

T. +34 93 774 57 09  
F. +34 93 774 18 33  
neu@rami-system.es  
www.rami-system.es